

# **Pipe**



## Product: CP-09-9

Application Double Wall Corrugated Pipe

Type Lead

Content(PbO) 28.5 - 31.5 % Typical Addition 4.0 - 6.0\*\*\* Lubrication Flake Form

### **Typical Formulation**

Material	Double Wall Corrugated Pipe	
PVC K68	100	
CPE	8-9	
CaCO <sub>3</sub>	20-30	
CP-09-9	4.0-6.0	
ACR Processing Aid	1.0-2.0	
Pigment	As Needed	

#### **Properties**

CP-09-9 is an onepack stabilizer applied in double wall corrugated pipe extrusion. It provides excellent processing performance to produce double wall corrugated pipe with high efficiency and enhanced physical properties.

CP-09-9 is supplied in low dust flake form which should be mixed in a high speed mixer to a discharge temperature of 120 °C and in low speed mixer to a discharge temperature of 40 °C.

All raw materials and every batch of one pack are tested to a high standard to ensure product consistency and meet the high quality demands of the customer. A quality assurance certificate can be provided for each product batch according to customer's request and supported by our ISO 9001:2008 Quality management system.

#### **Package**

3 in 1 plastic/paper bag(25kg N.W) or plastic woven container sack. Period of quatity guarantee is one year.

#### Storage

Stored in dry place, to avoid high temperature, kept away from sulfide.

Email: angel.cai@njchem.net

Fax: (025) 85315451 Web: www.njchem.net